

PRO-VAC 575-B-15

RELEASE FILM

High temperature fluoropolymer release film

Description:

- Designed for high temperature curing of advanced composite materials.
- Compatible for use with a wide range of commonly used resins systems in the oven and autoclave.
- High strength and toughness with excellent release properties.
- Offered as Standard P3 perforation pattern and non-perforated.



Technical data:

Part number	PRO-VAC 575-B-15		
Thickness	15 +/- 10%	μ	ISO 4593
Width	1530 -0+2%	mm	
Length	153 +/- 2%	m	
Tensile strength (break)	MD >40	N/mm ²	EN ISO 527-3
Tensile strength (break)	TD >40	N/mm ²	EN ISO 527-3
Tensile Strain (break)	MD >100	%	EN ISO 527-3
Tensile Strain (Break)	TD >100	%	EN ISO 527-3
Max use temperature	230	°C	

*A illustration of our Perforation specification can be issued on request.

Packaging and storage

Film is supplied in strong bubble plastic.
Store in original packaging.



HF Industri & Marine ApS

HF Industri & Marine ApS Gotlandsvej 6 5700 Svendborg Denmark
Phone: +45 62 20 13 12 • Fax: +45 62 20 14 77 • info@hfmarine.dk • www.hfmarine.dk