

PRO-VAC 910 R

RELEASE FILM

High temperature fluoropolymer (FEP) release film

Description:

- Designed for high temperature curing of advanced composite materials.
- Compatible for use with a wide range of commonly used resins systems in the oven and autoclave.
- Offered as Standard P3 perforation pattern and non-perforated.



Technical data:

Part number	PRO-VAC 910-R		
Thickness	13, 20, 25 +/- 10%	μ	ISO 4593
Width	1220-1530 -0+2% mm	mm	
Tensile strength (break)	MD / TD > 20	N/mm ²	ASTM D882
Elongation (break)	280	≥	ASTM D882
Max use temperature	260	°C	Internal

*A illustration of our Perforation specification is on the website.

Packaging and storage

Film is supplied in strong bubble plastic.
Store in original packaging.